

## FasTrack 80/80

FasTrack 8080 Woven Geotextile, 9000N, 356g/m<sup>2</sup> - 5.25m x 100m roll



UK  
CA CE

### DESCRIPTION

FasTrack 8080 Woven Geotextile, 9000N, 356g/m<sup>2</sup> - 5.25m x 100m roll

## SPECIFICATION

### General information

Stock code	GTSG/FASTRACK/8080
Range	FasTrack
Third party certified	UKCA CE
Roll sizes	5.25m x 100m
Geotextile product range	FasTrack

### Geotextile properties

Material		Polypropylene
Tensile strength (MD)	EN ISO 10319	80kN/m
Tensile strength (CMD)	EN ISO 10319	80kN/m
Elongation at max load (MD)	EN ISO 10319	15%
Elongation at max load (CMD)	EN ISO 10319	10%
Static puncture resistance	EN ISO 12236	9kN
Dynamic perforation resistance	EN ISO 13433	9mm

<b>CBR puncture resistance</b>	EN ISO 12236	9000N
<b>Dynamic cone drop</b>	EN ISO 13433	9mm
<b>Water permeability</b>	EN ISO 11058	10L/m <sup>2</sup> .s
<b>Characteristic opening size</b>	EN ISO 12956	230µm
<b>Thickness under 2kPa</b>	EN ISO 9863-1	1.3mm
<b>Weight</b>	EN ISO 9864	356g/m <sup>2</sup>

1. Wrekin Products Ltd is continually seeking to improve our products and therefore reserves the right to alter product specifications without prior notice.
2. It is the responsibility of all users to satisfy themselves the above data is current.
3. Installation details are available on request.
4. All Wrekin products are supplied subject to our [Terms and Conditions of Sale](#)

